

# High-Temperature Welding Electrodes

according to DIN EN 1599, DIN 8575 and AWS A 5.5

## **KOMPLEX W**

Stick electrode including 0.5% Mo for welds of identical and similar steels (e.g. 16Mo3), rutile-coated

## **MOB**

Stick electrode including 0.5% Mo for welds of identical and similar steels (e.g. 16Mo3), basic-coated

## **CROMO 1B**

Stick electrode including 1% Cr and 0.5% Mo for welds of identical and similar steels (e.g. 13CrMo4-5), basic-coated

## **IMPULS**

Stick electrode including 0.6% Ni and 0.4% Mo for welds of identical and similar steels, basic-coated

## **CROMO 1R**

Stick electrode including 1% Cr and 0.5% Mo for welds of identical and similar steels (e.g. 13CrMo4-5), rutile-coated

## **CROMO 2B**

Stick electrode including 2,2% Cr and 1% Mo for welds of identical and similar steels (e.g. 10CrMo9-10), basic-coated