


Processing information

Re-drying: 300 - 350 °C/2 h

Welding positions:



Polarity:



Whether preheating is required depends on the base material, otherwise not necessary. Interpass temperature max. 150 °C.

Application

Electrode for joint welding on low-carbon, unsta-
bilised and stabilised austenitic, chemically stable
chromium-nickel-molybdenum steel at working
temperatures of up to 400 °C. This stainless steel
electrode is also suitable for claddings of similar
alloys.

Field



Characteristic
rutile-coated,
core wire-alloyed

Standards

ISO 3581-A
E 19 12 3 L R 12
AWS A 5.4
E 316 L-16

Material no.

1.4430

Approvals



Materials

1.4401	X 5 CrNiMo 17-12-2	1.4435	X 2 CrNiMo 18-14-3
1.4404	X 2 CrNiMo 17-12-2	1.4436	X 3 CrNiMo 17-13-3
1.4406	X 2 CrNiMoN 17-11-2	1.4571	X 6 CrNiMoTi 17-12-2
1.4408	GX 5 CrNiMo 19-11-2	1.4580	X 6 CrNiMo- Nb 17-12-2
1.4409	GX 2 CrNiMo 19-11-2	1.4429	X 2 CrNiMoN 17-13-03
-	AISI 316 AISI 316L AISI 316 Cb AISI 316Ti		

All Weld Metal Mechanical Properties

Heat Treatment	AW				
Structure	Austenite with approx. 8 % ferrite				
Weld Metal Composition [%]					
C	Si	Mn	Cr	Ni	Mo
0,02	0,9	0,8	19	12,5	2,7
Yield Strength Rp 0,2 [MPa]		> 350			
Tensile Strength Rm [MPa]		> 550			
Elongation A5 [%]		> 30			
Charpy Impact Value ISO-V (J/RT)		> 60			

Welding Current, Packaging

Item no.	Dm./Länge [mm]	Amperage [A]	kg/Pack	≈ Piece/Pack	kg/1000 Pc.
00.703.162	1,60/250	40 - 60	3,0	500	6,0
00.703.200	2,00/300	60 - 80	4,0	348	11,5
00.703.250	2,50/300	80 - 100	4,0	220	18,2
00.703.323	3,25/350	100 - 130	5,0	139	36,0
00.703.403	4,00/350	120 - 160	5,0	93	53,8
00.703.504	5,00/450	160 - 200	6,0	55	109,1



.kjellberg.de

Kjellberg Finsterwalde
Elektroden und
ZusatzMaterials GmbH
Ludwig-Erhard-Str. 12
03238 Finsterwalde
Germany

Copyright © 2018 | E18-12-37E
Kjellberg Finsterwalde

+49 3531 50768-0

✉ elektrode@kjellberg.de