


Processing information

When welding heat-resistant Cr-steels preheating and interpass temperature of 200 to 400 °C is recommended, otherwise no preheating. Post weld heat treatment only in dependence of base material necessary.

Re-drying: 250 - 300 °C/2 h
(if required)

Welding positions:



Polarity:



Application

Electrode for joint welding and surfacing on heat-resistant chromium-nickel steel and cast steel of the same or similar alloy at working temperatures of up to 1200 °C, for tough joints, intermediate and filler layers when welding chromium steel and cast steel. Further, this electrode is suitable for joining unalloyed and low-alloyed steel and cast steel or stainless and heat-resistant chromium steel and cast steel with austenitic steel and cast steel at working temperatures of up to 300 °C.

The weld metal does not have sufficient resistance against reducing, sulphur-containing and carburising gases. A cover layer with Finox 4820 AC should be applied in these cases.

Field



Characteristic
basic-coated,
core wire-alloyed

Standards
ISO 3581-A
E 25 20 B 22

AWS A 5.4
E 310-15

Material no.
14842

Materials

1.4710	GX 30 CrSi 7	1.4833	X 12 CrNi 23-13
1.4713	X 10 CrAlSi 7	1.4840	GX 15 CrNi 25-20
1.4724	X 10 CrAlSi13	1.4841	X 15 CrNiSi 25-21
1.4742	X 10 CrAlSi18	1.4845	X 8 CrNi 25-21
1.4762	X 10 CrAlSi 25	1.4846	X 40 CrNi 25-21
1.4828	X 15 CrNiSi 20-12	-	AISI 310, 310S, 314

All Weld Metal Mechanical Properties

Heat Treatment	AW			
Structure	Austenite			
Weld Metal Composition [%]				
C	Si	Mn	Cr	Ni
0,1	0,8	2,5	25	20
Yield Strength Rp 0,2 [MPa]		> 350		
Tensile Strength Rm [MPa]		> 550		
Elongation A5 [%]		> 30		
Charpy Impact Value ISO-V RT [J]		> 80		

Welding Current, Packaging

Item no.	Dm./Länge [mm]	Amperage [A]	kg/Pack	≈ Piece/Pack	kg/1000 Pc.
00.713.250*	2,50/300	80 - 100	4,0	266	15,0
00.713.323*	3,25/350	100 - 130	5,0	170	29,4
00.713.403*	4,00/350	120 - 160	5,0	113	44,2

* This product is not a standard stock article. All dimensions are produced only to customer order.
Ask for an individual quotation.



.kjellberg.de

Kjellberg Finsterwalde
Elektroden und
ZusatzMaterials GmbH
Ludwig-Erhard-Str. 12
03238 Finsterwalde
Germany

Copyright © 2018 | E18-12-30E
Kjellberg Finsterwalde

+49 3531 50768-0

elektrode@kjellberg.de