

### Processing information

Welding positions:



Polarity:



### Application

High-efficiency electrode, especially designed for fillet welds, filler and cover passes in welding positions PA and PB in engineering, ship and bridge building. It allows very cost-efficient welding due to a high run-out length. It is characterised by a smooth arc, very clean seam surfaces and self-lifting slag.

### Field



**Characteristic**  
**rutile-coated,**  
**160 % recovery**

### Standards

**ISO 2560-A**  
**E42 0 Z RR 53**  
**AWS A 5.1**  
**E 7024**

### Approvals



Materials	
Construction steels	S235 - S355
Ship steels	A, B, D, A32/36, D32/36
Boiler steels	P195 - P275
Pipe steels	L210 - L245
Cast steels	GE200, GE240, GP240
Reinforcing steels	BSt 420 BSt 500

All Weld Metal Mechanical Properties				
<b>Heat Treatment</b>				AW
<b>Weld Metal Composition [%]</b>				
C	Si	Mn	Ni	
0,09	0,4	0,9	0,7	
<b>Yield Strength Re [MPa]</b>				> 440
<b>Tensile Strength Rm [MPa]</b>				510-560
<b>Elongation A5 [%]</b>				> 22
<b>Charpy Impact Value ISO-V [J/0°C]</b>				> 47

### Welding Current, Packaging

Item no.	Dia./Length [mm]	Amperage [A]	kg/Pack	= Piece/Pack	kg/1000 Pc.
00.820.324	3,25/450	110 - 150	6,0	88	68,2
00.820.404	4,00/450	140 - 190	5,6	55	101,8
00.820.504	5,00/450	180 - 230	6,0	38	157,9



.kjellberg.de

Kjellberg Finsterwalde  
Elektroden und  
ZusatzMaterials GmbH  
Ludwig-Erhard-Str. 12  
03238 Finsterwalde  
Germany

Copyright © 2018 | E18-12-10E  
Kjellberg Finsterwalde

+49 3531 50768-0

elektrode@kjellberg.de