


Processing information

Whether preheating is required depends on the base material, otherwise not necessary. Interpass temperature max. 150 °C.

Re-drying: 300 - 350 °C/2 h

Welding positions:



Polarity:



Application

Electrode for joint welding on unstabilised and stabilised austenitic, chemically stable chromium-nickel steel at working temperatures of up to 400 °C, for corrosion-resistant chromium steel as well as claddings of similar alloys.

Field



Characteristic
rutile-coated,
core wire-alloyed

Standards
ISO 3581-A
E 19 9 Nb R 12
AWS A 5.4
E 347-16

Material no.
1.4551

Approvals



Materials			
1.4301	X 5 CrNi 18-10	1.4550	X 6 CrNiNb 18-10
1.4306	X 2 CrNi 19-11	1.4552	GX 5 CrNiNb 19-11
1.4311	X 2 CrNiN 18-10	-	AISI 304 AISI 304L
1.4541	X 6 CrNiTi 18-10	-	AISI 304LN AISI 321 AISI 347

All Weld Metal Mechanical Properties	
Heat Treatment	AW
Structure	Austenite with approx. 8 % ferrite
Weld Metal Composition [%]	
C	Si
0,02	0,9
Mn	Cr
0,8	19,0
Ni	Nb
9,5	0,3
Yield Strength Rp 0,2 [MPa]	
> 350	
Tensile Strength Rm [MPa]	
> 550	
Elongation A5 [%]	
> 25	
Charpy Impact Value ISO-V [J/RT]	
> 55	

Welding Current, Packaging

Item no.	Dm./Länge [mm]	Amperage [A]	kg/Pack	≈ Piece/Pack	kg/1000 Pc.
00.702.250	2,50/300	80 - 100	4,0	224	17,9
00.702.323	3,25/350	100 - 130	5,0	139	36,0
00.702.403*	4,00/350	120 - 160	5,0	92	54,3

* This product is not a standard stock article. Produced only to customer order. Ask for an individual quotation.



||| .kjellberg.de

Kjellberg Finsterwalde
Elektroden und
ZusatzMaterials GmbH
Ludwig-Erhard-Str. 12
03238 Finsterwalde
Germany

Copyright © 2018 | E18-12-35E
Kjellberg Finsterwalde

+49 3531 50768-0

✉ elektrode@kjellberg.de