


### Processing information

Welding positions:



Polarity:



### Application

Electrode for a wide range of applications in engineering, pipeline and container construction and ship building. It is characterised by excellent ignition, a smooth arc and low spatter. The electrode provides a finely rippled seam surface, flat concave fillets and self-lifting slag.

Field



**Characteristic  
rutile-coated**

**Standards  
ISO 2560-A  
E35 0 RR 12  
AWS A 5.1  
E 6013**

Approvals



### Materials

Construction steels	S235 - S355
Ship steels	A, B, D, A32/36, D32/36
Boiler steels	P195 - P275
Pipe steels	L210 - L245
Cast steels	GE200, GE240
Reinforcing steels	BSt 420

### All Weld Metal Mechanical Properties

Heat Treatment	AW	
Weld Metal Composition [%]		
C	Si	Mn
0,08	0,25	0,4
Yield Strength Re [MPa]	> 360	
Tensile Strength Rm [MPa]	450 - 550	
Elongation A5 [%]	> 22	
Charpy Impact Value ISO-V [J/0°C]	> 55	

### Welding Current, Packaging

Item no.	Dia./Length [mm]	Amperage [A]	kg/Pack	≈ Piece/Pack	kg/1000 Pc.
00.240.253*	2,50/350	80 - 100	4,8	230	20,9
00.240.323*	3,25/350	100 - 130	4,8	137	35,0

\* This product is not a standard stock article. All dimensions are produced only to customer order. Ask for an individual quotation.



.kjellberg.de

Kjellberg Finsterwalde  
Elektroden und  
ZusatzMaterials GmbH  
Ludwig-Erhard-Str. 12  
03238 Finsterwalde  
Germany

Copyright © 2018 | E18-12-05E  
Kjellberg Finsterwalde

+49 3531 50768-0

elektrode@kjellberg.de